

LA-CO Industries
1201 Pratt Blvd.
Elk Grove Village , IL 60007

Request ID: R-20181031-030
Date: 11/07/2018
PO Number: PPO269855 Revision 1

Bhopinder Parmar

Client Description: Thermomelt Stick

Page 1 of 2

Sample No.: S-181031-034 Customer ID: 175F, Batch# 083118A

Tests	Results/Units	Method	Specification Limits	Specification Description
As	<2 ppm	ICP-MS	min: 0 / max: 2	Thermomelt Sticks
Bi	<10 ppm	ICP-MS	min: 0 / max: 250	Thermomelt Sticks
Br	<10 ppm	Parr Bomb followed by Ion Chromatography	min: 0 / max: 200	Thermomelt Sticks
Cd	<10 ppm	ICP-MS	min: 0 / max: 250	Thermomelt Sticks
Cl	100 ppm	Parr Bomb followed by Ion Chromatography	min: 0 / max: 200	Thermomelt Sticks
F	<10 ppm	Parr Bomb followed by Ion Chromatography	min: 0 / max: 200	Thermomelt Sticks
Hg	<1 ppm	Cold Vapor AA	min: 0 / max: 1	Thermomelt Sticks
I	<10 ppm	Parr Bomb followed by Specific Ion Electrode	min: 0 / max: 200	Thermomelt Sticks
In	<10 ppm	ICP-MS	min: 0 / max: 200	Thermomelt Sticks
LACO Low Melting Point Metals	<73 ppm	Calculation	min: 0 / max: 300	Thermomelt Sticks

Methods noted with an * fall outside of NSL's ISO 17025 Scope of Accreditation.

All quantitative analytical results are subject to variability due to the nature of testing. Estimated Uncertainty data is available upon request.

These results relate only to the items tested and this report shall not be reproduced, except in full, without the written consent of NSL Analytical Services, Inc.

The recording of false, fictitious, or fraudulent statements or entries on this document may be punished as a felony under the federal statutes, including Federal Law, Title 18, Chapter 47.

Reporting Officer :

NSL Analytical Services
4450 Cranwood Parkway
Cleveland, Ohio 44128



Roxanne Skinner, Technical Specialist

For current Terms and Conditions, please visit
<http://nslanalytical.com/terms-and-conditions>

LA-CO Industries
1201 Pratt Blvd.
Elk Grove Village , IL 60007

Request ID: R-20181031-030
Date: 11/07/2018
PO Number: PPO269855 Revision 1

Bhopinder Parmar

Client Description: Thermomelt Stick

Page 2 of 2

Sample No.: S-181031-034 Customer ID: 175F, Batch# 083118A

Tests	Results/Units	Method	Specification Limits	Specification Description
P	<50 ppm	ICP-MS	min: 0 / max: 200	Thermomelt Sticks
Pb	<10 ppm	ICP-MS	min: 0 / max: 200	Thermomelt Sticks
S	30 ppm	Parr Bomb followed by Ion Chromatography	min: 0 / max: 200	Thermomelt Sticks
Sb	<10 ppm	ICP-MS	min: 0 / max: 200	Thermomelt Sticks
Sn	<10 ppm	ICP-MS	min: 0 / max: 200	Thermomelt Sticks
Total Halogens	<130 ppm	Calculation	min: 0 / max: 200	Thermomelt Sticks
Zn	<10 ppm	ICP-MS	min: 0 / max: 250	Thermomelt Sticks

The Low Melt Point calculation includes the following elements: Sb, Bi, Cd, Pb, Sn, Zn, Hg, As, In.

The analysis performed conforms to the specifications indicated

Methods noted with an * fall outside of NSL's ISO 17025 Scope of Accreditation.

All quantitative analytical results are subject to variability due to the nature of testing. Estimated Uncertainty data is available upon request.

These results relate only to the items tested and this report shall not be reproduced, except in full, without the written consent of NSL Analytical Services, Inc.

The recording of false, fictitious, or fraudulent statements or entries on this document may be punished as a felony under the federal statutes, including Federal Law, Title 18, Chapter 47.

Reporting Officer :

NSL Analytical Services
4450 Cranwood Parkway
Cleveland, Ohio 44128



Roxanne Skinner, Technical Specialist

For current Terms and Conditions, please visit
<http://nslanalytical.com/terms-and-conditions>